

What is claimed is:

1. A process for increasing the hydrophilicity of a polymer comprising adding to the polymer an effective amount of a di- C₁₀₋₁₂ fatty acid ester of polyethylene glycol.
2. The process of claim 1 wherein the polyethylene glycol has a molecular weight of from about 300 to about 600.
3. The process of claim 2 wherein the polyethylene glycol has a molecular weight of about 400.
4. The process of claim 1 wherein the effective amount is from about 0.5% to about 10% by weight of the polymer.
5. The process of claim 4 wherein the effective amount is from about 0.5% to about 5% by weight of the polymer.
6. The process of claim 5 wherein the effective amount is from about 1.0% to about 2.5% by weight of the polymer.
7. The process of claim 1 wherein the ester is di-laurate ester of polyethylene glycol.
8. The process of claim 7 wherein the polyethylene glycol has a molecular weight of about 400.
9. The process of claim 1 wherein the ester is di-decanoate ester of polyethylene glycol.
10. A process for making a synthetic polypropylene fiber having increased hydrophilicity comprising the steps of: (1) adding an effective amount of a di- C₁₀₋₁₂ fatty acid ester of polyethylene glycol to polypropylene to form a mixture; (2) heating the mixture to form a melt; and

(3) spinning the melt into a fiber.

11. The process of claim 10 wherein the polyethylene glycol has a molecular weight of from about 300 to about 600.

5

12. The process of claim 11 wherein the polyethylene glycol has a molecular weight of about 400.

10

13. The process of claim 10 wherein the effective amount is from about 0.5% to about 10% by weight of the polymer.

14. The process of claim 13 wherein the effective amount is from about 0.5% to about 5% by weight of the polymer.

15

15. The process of claim 14 wherein the effective amount is from about 1.0% to about 2.5% by weight of the polymer.

16. The process of claim 10 wherein the ester is di-laurate ester of polyethylene glycol.

20

17. The process of claim 16 wherein the polyethylene glycol has a molecular weight of about 400.

25

18. The process of claim 10 wherein the ester is di-decanoate ester of polyethylene glycol.

19. The process of claim 18 wherein the polyethylene glycol has a molecular weight of about 400.

30

20. A non-woven fabric having increased hydrophilicity which comprises synthetic fibers comprised of a polymer containing an effective amount of a di- C₁₀₋₁₂ fatty acid ester of polyethylene glycol.

21. The non-woven fabric of claim 20 wherein the polyethylene glycol

has a molecular weight of from about 300 to about 600.

22. The non-woven fabric of claim 21 wherein the polyethylene glycol has a molecular weight of about 400.

5

23. The non-woven fabric of claim 20 wherein the effective amount is from about 0.5% to about 10% by weight of the polymer.

10

24. The non-woven fabric of claim 23 wherein the effective amount is from about 0.5% to about 5% by weight of the polymer.

25. The non-woven fabric of claim 24 wherein the effective amount is from about 1.0% to about 2.5% by weight of the polymer.

15

26. The non-woven fabric of claim 20 wherein the ester is di-laurate ester of polyethylene glycol.

20

27. The non-woven fabric of claim 26 wherein the polyethylene glycol has a molecular weight of about 400.

28. The non-woven fabric of claim 20 wherein the ester is di-decanoate ester of polyethylene glycol.

25

29. The non-woven fabric of claim 28 wherein the polyethylene glycol has a molecular weight of about 400.

30. The non-woven fabric of claim 20 wherein the polymer is polyethylene.

30

31. The non-woven fabric of claim 20 wherein the polymer is polypropylene.